

solvent-free high-tack linoleum adhesive

DESCRIPTION

EP 67L is a high-tack adhesive for indoor installations of sheet linoleum.

USE

For the installation of:

Sheet goods:
linoleum

GUIDELINES AND RECOMMENDATIONS

- Surfaces shall be smooth, sound, dry, well fastened, clean and free from dust, oil, grease, paint, tar, wax or any deleterious substances which may prevent or reduce adhesion. Refer to flooring manufacturer's installation instructions for detailed information.
- Concrete floors must be completely cured and dry. It is essential that all concrete slabs be tested for moisture using either the ASTM F1869 Anhydrous Calcium Chloride test or the ASTM F2170 Relative Humidity in situ test. If moisture vapour emission exceeds 3 lbs. per 1000 SF in 24 hours per ASTM F1869 or relative humidity exceeds 75% per ASTM F2170, do not use this adhesive.
- Do not apply over gypsum based surfaces.
- Do not use when substrate temperature is below 10°C or above 30°C.

TECHNICAL DATA:

COVERAGE

4 - 5 SY per litre

PACKAGING

15 litre pail 44 lbs

SHELF-LIFE

2 years in unopened container

PROTECT FROM FREEZING

VOC

24.0g / litre
Complies with SCAQMD Rule 1168

SETTING TIME

Open Time: 10 - 25 minutes depending on temperature, humidity, substrate, trowel size and jobsite conditions.
Ready for traffic in 24 hours and for heavier traffic in 3 days.

APPLICATION

1. Use the flooring manufacturer's recommended notched trowel size. 3/32" x 3/32" x 3/32" is typical for linoleum. The recommended notched trowel is important, but it is only a guide. The absorption of the subfloor needs to be taken into account: the less absorbent the surface is the smaller the notch. Too much adhesive will cause tiles to move during installation or air pockets to gather beneath the sheet material.
2. Spread adhesive evenly. Do not spread more adhesive than can be covered in 30 minutes.
3. For best results, leave adhesive to flash for 15 - 20 minutes depending on site conditions.
4. Roll floor covering across width and length with a 70 kg (150 lb) roller.
5. Do not walk over a newly laid installation before 24 hours. For heavy traffic, do not use before 72 hours.

CLEANING

Fresh adhesive must be removed immediately with a damp cloth. Dried adhesive may be removed with a non-flammable solvent.

We shall not be liable for incidental and consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instructions or for other than the intended use. Before using, user shall determine the suitability of the product for its intended use and user alone assumes all risks and liability whatsoever in connection therewith. Our liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from date it was, or reasonably should have been, discovered

Contacts:
www.ervparent.com
info@ervparent.com

Vancouver
tel: 604-525-4142
fax: 604-525-3777

Calgary
403-253-3145
403-255-1127

Edmonton
780-453-3466
780-452-8486

Regina
306-721-2383
306-721-2454

Winnipeg
204-475-3555
204-452-5826